


WHAT IS CLAIMED IS:


2. A process for the synthesis of polymers selected from the group consisting of:

1. A process for the synthesis of polymers selected from the group



Formula A

and




Formula B

comprising contacting:


- (i) a monomer having repeating units, Q, selected from the group consisting of vinyl monomers of structure $\text{CH}_2=\text{CUV}$, maleic anhydride, N-alkylmaleimide, N-arylmaleimide, dialkyl fumarate and cyclopolymerizable monomers;

- (ii) a thiocarbonylthio compound selected from:



Formula C

and



Formula D

having a chain transfer constant greater than about 0.1; and

- (iii) free radicals produced from a free radical source; and controlling the polydispersity of the polymer being formed by varying the ratio of the number of molecules of (ii) to the number of molecules of (iii);


the polymer of Formula A being made by contacting (i), (ii)C and (iii) and the polymer of Formula B being made by contacting (i), (ii) D and (iii);

5 wherein:

Z is selected from the group consisting of hydrogen, chlorine, optionally substituted alkyl, optionally substituted aryl, optionally substituted heterocyclyl, optionally substituted alkylthio, optionally substituted alkoxy-carbonyl, optionally substituted aryloxy-carbonyl (-COOR"), carboxy (-COOH), optionally substituted acyloxy (-O₂CR"), optionally substituted carbamoyl (-CONR"2), cyano (-CN), dialkyl- or diaryl- phosphonato [-P(=O)OR"2], dialkyl- or diaryl-phosphinato [-P(=O)R"2], and a polymer chain formed by any mechanism;

15 Z' is a m-valent moiety derived from a member of the group consisting of optionally substituted alkyl, optionally substituted aryl and a polymer chain; where the connecting moieties are selected from the group that consists of aliphatic carbon, aromatic carbon, and sulfur;

Q is selected from the group consisting of



20

and

repeating units from maleic anhydride, N-alkylmaleimide, N-arylmaleimide, dialkyl fumarate and cyclopolymerizable monomers;

25 U is selected from the group consisting of hydrogen, halogen, optionally substituted C₁-C₄ alkyl wherein the substituents are independently selected from the group that consists of hydroxy, alkoxy, aryloxy (OR"), carboxy, acyloxy, aryloxy (O₂CR"), alkoxy-carbonyl and aryloxy-carbonyl (CO₂R");

30 V is selected from the group consisting of hydrogen, R", CO₂H, CO₂R", COR", CN, CONH₂, CONHR", CONR"2, O₂CR", OR" and halogen;

2
R is selected from a group consisting of optionally substituted alkyl; an optionally substituted saturated, unsaturated or aromatic carbocyclic or heterocyclic ring; optionally substituted alkylthio; optionally substituted alkoxy; optionally substituted dialkylamino; an organometallic species; and a polymer chain prepared by any polymerization mechanism; in compounds C and D, R• is a
5 free-radical leaving group that initiates free radical polymerization;

R" is selected from the group consisting of optionally substituted C₁-C₁₈ alkyl, C₂-C₁₈ alkenyl, aryl, heterocyclyl, aralkyl, alkaryl wherein the substituents
10 are independently selected from the group that consists of epoxy, hydroxy, alkoxy, acyl, acyloxy, carboxy (and salts), sulfonic acid (and salts), alkoxy- or aryloxy-carbonyl, isocyanato, cyano, silyl, halo, and dialkylamino;

q is 1 or an integer greater than 1;

p is 1 or an integer greater than 1; when $p \geq 2$ then $R=R'$;

m is an integer ≥ 2 ; and


20 R' is a p-valent moiety selected from a member of the group consisting of optionally substituted alkyl, optionally substituted aryl and a polymer chain; where the connecting moieties are selected from the group consisting of aliphatic carbon, aromatic carbon, silicon, and sulfur; in compounds C and D, R'• is a free radical leaving group that initiates free radical polymerization.

2. A process according to Claim 1 comprising controlling polydispersity by varying the ratio of the number of molecules of (ii) to (iii) as follows:

- 5 (a) lower polydispersity by increasing the ratio of (ii) to (iii); and
 (b) increase polydispersity by decreasing the ratio of (ii) to (iii).

3. A process according to Claim 2 comprising increasing the ratio of (ii) to (iii) and obtaining a polymer having a polydispersity below about 1.5.


4. A process according to Claim 1 comprising selecting the following monomer repeating unit:




from (i).

5. A process according to Claim 1 comprising selecting the monomer units Q and the value of q so that when $q \geq 1$ and Q is a single monomer species, then the polymer is homopolymer; when $q \geq 2$ and Q is selected from 2 or more different monomer species in irregular sequence then the polymer is copolymer; and when $q \geq 2$ and Q is selected from 2 or more different monomer species in which each different monomer or group of monomers appears in a discrete sequence then the polymer is block copolymer.


6. A process according to Claim 1 wherein the thiocarbonylthio compound is selected from the group consisting of:




(3)



(4)




(5)




(7)




(8)




(11)




(12)




(14)




(16)




(18)




(20)




(22)




(6)




(9)




(10)




(13)




(15)




(17)




(19)




(21)




(23)




(24)




(25)



(26)




(27)



(28)


and




(29)

10 wherein Z is phenyl.


7. A chain transfer agent selected from the group consisting of:




(5)




(6)




(7)




(9)




(8)




(10)














(11)



(14)



(15)

[illegible][illegible][illegible][illegible][illegible]


	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44	45	46	47	48	49	50	51	52	53	54	55	56	57	58	59	60	61	62	63	64	65	66	67	68	69	70	71	72	73	74	75	76	77	78	79	80	81	82	83	84	85	86	87	88	89	90	91	92	93	94	95	96	97	98	99	100
1	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44	45	46	47	48	49	50	51	52	53	54	55	56	57	58	59	60	61	62	63	64	65	66	67	68	69	70	71	72	73	74	75	76	77	78	79	80	81	82	83	84	85	86	87	88	89	90	91	92	93	94	95	96	97	98	99	100

wherein:

Z is selected from the group consisting of hydrogen, chlorine, optionally substituted alkyl, optionally substituted aryl, optionally substituted heterocyclyl, optionally substituted alkylthio, optionally substituted alkoxy-carbonyl or optionally substituted aryloxy-carbonyl (-COOR"), carboxy (-COOH), optionally substituted acyloxy (-O₂CR"), optionally substituted carbamoyl (-CONR"2), cyano (-CN), dialkyl- or diaryl- phosphonato [-P(=O)OR"2], dialkyl- or diaryl- phosphinato [-P(=O)R"2], and a polymer chain formed by any mechanism;

Z' is a m-valent moiety derived from a member of the group consisting of optionally substituted alkyl, optionally substituted aryl and a polymer chain; where the connecting moieties are selected from the group that consists of aliphatic carbon, aromatic carbon, and sulfur;

Q is selected from the group consisting of



and

repeating units from maleic anhydride, N-alkylmaleimide, N-arylmaleimide, dialkyl fumarate and cyclopolymerizable monomers;

U is selected from the group consisting of hydrogen, halogen, optionally substituted C₁-C₄ alkyl, wherein the substituents are independently selected from the group consisting of hydroxy, alkoxy, aryloxy (OR"), carboxy, acyloxy, aryloxy (O₂CR"), alkoxy-carbonyl and aryloxy-carbonyl (CO₂R");

V is selected from the group consisting of hydrogen, R", CO₂H, CO₂R", COR", CN, CONH₂, CONHR", CONR"2, O₂CR", OR" and halogen;

R is selected from the group consisting of optionally substituted alkyl; an optionally substituted saturated, unsaturated or aromatic carbocyclic or heterocyclic ring; optionally substituted alkylthio; optionally substituted alkoxy; optionally substituted dialkylamino; an organometallic species; and a polymer chain prepared by any polymerization mechanism; R• being derived from a free radical leaving group that initiates free radical polymerization;

B' 5 R" is selected from the group consisting of optionally substituted C₁-C₁₈ alkyl, C₂-C₁₈ alkenyl, aryl, heterocyclyl, aralkyl, alkaryl wherein the substituents are independently selected from the group that consists of epoxy, hydroxy, alkoxy, acyl, acyloxy, carboxy (and salts), sulfonic acid (and salts), alkoxy- or aryloxy-carbonyl, isocyanato, cyano, silyl, halo, and dialkylamino;

q is 1 or an integer greater than 1;

10 p is 1 or an integer greater than 1; when $p \geq 2$, then $R=R'$;

m is an integer ≥ 2 ; and

15 R' is a p-valent moiety derived from a member of the group consisting of optionally substituted alkyl, optionally substituted aryl and a polymer chain; where the connecting moieties are selected from the group consisting of aliphatic carbon, aromatic carbon, silicon, and sulfur; R'• being derived from a free radical leaving group that initiates free radical polymerization.

20 9. A polymer according to Claim 8 selected from the group consisting of random, block, graft, star and gradient copolymer.

10. A polymer according to Claim 9 having end group functionality.

Add A31